

TECHNICAL DATA

Curing Temperature	:	5°C	15°C	30°C
Initial Set	:	5 - 7 min	3 - 5 min	1- 3min
Minimum application	:	3°C		
Compressive strength(MPA)		1hr.	1hr.	24hrs

(Tested on 50 mm cubes

with show set	:	50	60	67.5
---------------	---	----	----	------

as per BS : 7861

Youngs Modulus(MPa)	:			>6.5
---------------------	---	--	--	------

Pull Out strength

Measured on 22 mm bolt, 50 mm encapsulation

In 28 mm dia hole with show set resin (kN)				>72
--	--	--	--	-----

AVAILABILITY : Three grades i.e. Fast, Medium& Slow

SELF LIFE : Three month from the date of manufacture when stored
 Between 20 & 25°C.

PACKING : Available in three grades in range of lengths, speed and
 Diameters, Packed in cardboard cartons.

STORAGE : Store in a cool, dry place preferably below 25°C.

TECHNICAL SUPPORT

Buildtech Products offers a complete technical & field support service.